AMENDMENTS TO THE CLAIMS

- 1. (currently Amended) Mono or multilayered polypropylene cast film comprising at least one layer wherein said at least one layer comprises a two component polymer composition of a first component I and a second component II, characterised in that the first component I is a high crystallinity propylene homopolymer and the second component II is a heterophasic propylene copolymer wherein the high crystallinity propylene homopolymer has a stereoregularity of 94 to 99%.
- 2. (Cancelled)
- 3. (Currently Amended) Cast film according to claim 2 characterised in that, Claim 1, wherein the high crystallinity propylene homopolymer contains 98 to 100% by weight of propylene units.
- 4. (Previously presented) Cast film according to claim 1 characterised in that, the high crystallinity propylene homopolymer has a melt flow index of 5 to 10 g/10min and a melting point of 150 to 170°C.
- 5. (Currently Amended)) Cast film according to <u>Claim 1</u>, characterised in that, the high crystallinity propylene homopolymer contains 1.5 to 5% by weight of xylene solubles.
- 6. (Previously presented) Cast film according to claim 1, characterised in that, heterophasic propylene copolymer comprises a propylene homopolymer matrix and a dispersed elastomeric rubber phase.
- 7. (Previously presented) Cast film according to claim 1, characterised in that, the heterophasic propylene copolymer contains 12 to 18% by weight of xylene solubles.
- 8. (Previously presented) Cast film according to claim 1, characterised in that, the heterophasic propylene copolymer has an ethylene content of 5 to 15% by weight, based on the weight of the heterophasic propylene copolymer
- 9. (Previously presented) Cast film according to claim 1, characterised in that, the heterophasic propylene copolymer has a melt flow index of 0.2 to 5g/10min.
- 10. (Previously presented) Cast film according to claim 1, characterised in that, the heterophasic propylene copolymer has a Vicat softening point of 145 to 155°C.

- 11. (Previously presented) Cast film according to claim 1, characterised in that, the heterophasic propylene contains less than 5 20% by weight of the elastomeric rubber phase, based on the weight of the heterophasic propylene copolymer
- 12. (Previously presented) Cast film according to claim 1, characterised in that, the dispersed elastomeric rubber phase is a ethylene propylene copolymer.
- 13. (Previously presented) Cast film according to claim 12, characterised in that, the ethylene propylene copolymer rubber has an ethylene content of 40 to 65%.
- 14. (Previously presented) Cast film according to claim 1, characterised in that, the two component polymer composition is a mixture of the two components.
- 15. (Previously presented) Cast film according to claim 1, characterised in that, the two component polymer composition is a blend of the two components.
- 16. (Previously presented) Cast film according to claim 1, characterised in that, the ratio of the two components I and II is in the range of from high crytallinity polypropylene (HCPP) to heterophasic propylene copolymer (HP), HCPP:HP = 90:10 to 50:50.
- 17. (Previously presented) Cast film according to claim 16, wherein said ratio is in the range from HCPP:HP = 80:20 to 60:40.
- 18. (Previously presented) Cast film according to claim 1, characterised in that, the base layer contains 80 to 100% by weight of the two components polymer composition, based on the weight of the layer.
- 19. (Previously presented) Cast film according to claim 1, characterised in that, the base layer containing the two components polymer composition is at least 50% of the overall film thickness.
- 20. (Previously presented) Cast film according to claim 1, characterised in that, a second layer containing 80 to 100% by weight of the two component polymer composition is provided on the first surface of the base layer.
- 21. (Previously presented) Cast film according to claim 1, characterised in that, a third layer containing 80 to 100% by weight of the two component polymer composition is provided on the second surface of the base layer.

3

Application No. 10/575,749 Reply to Office Action of September 18, 2008

- 22. (Previously presented) Cast film according to claim 1, characterised in that, one or two intermediate layers are provided between the outer layers and the base layer.
- 23. (Previously presented) Cast film according to claim 1, characterised in that, the base layer contains 1000 to 3000 ppm of a nucleating agent.
- 24. (Previously presented) Cast film according to claim 1, characterised in that, both cover layers contain an antistatic agent and a slip agent.
- 25. (Previously presented) Cast film according to claim 1, characterised in that, the antistatic agent is glycerol monostearate and the slip agent is oleamid and/or stereoamid.
- 26. (Previously presented) Label made from a cast film according to claim 1.
- 27. cancelled
- 28. cancelled
- 29. cancelled
- 30. cancelled
- 31. (Cancelled)
- 32. (Cancelled)